CHRYSO CONCRETE SOLUTIONS

CHRYSO®Plast 405

Normal Water Reducing Admixture

DESCRIPTION

CHRYSO*Plast 405 is a water-reducing admixture designed to improve the overall concrete performance for ReadyMix and paving applications. CHRYSO*Plast 405 provides good workability and improves hardened concrete durability.

Meets or exceeds the requirements of ASTM C-494 Type A and D

ADVANTAGES

- Improved Finish, Placement and Pumpability
- Increases early and ultimate compressive and flexural strengths
- Reduces cracking and shrinkage
- Improves Cementitious Material Performance (More PSI/lb)

FIELDS OF APPLICATION

- All Cement Types
- Ready Mix Concrete
- Hot Weather Concreting

METHOD OF USE

Dosage

- The recommended dosage rate for CHRYSO *Plast 405 is 3 to 6 oz/cwt (195 to 390 ml/100 kg) of cementitious material for a Type A and 4 to 7 oz/cwt (260 to 455 ml/100 kg) of cementitious material for a Type D.
- CHRYSO Plast 405 can be added with the initial water or, for optimum performance, on the wetted concrete. It should not be added with or on the dry cement.
- Dosage rates may vary when used in conjunction with other CHRYSO admixtures.
- Trial mixes should be conducted to determine the dosage rate needed.
- Because local job conditions vary, please contact your local CHRYSO sales representative for further assistance if using the product outside the recommended dosage ranges.



CHRYSO CONCRETE SOLUTIONS

CHRYSO®Plast 405

Normal Water Reducing Admixture

CHARACTERISTICS

Product Nature	Liquid
Color	Brown
Shelf life	9 months
CI [—] lons content	< 0,100 %
Specific gravity (25°C) in g/ml	1,144
pH (25°C)	5,30

This product does not contain any purposely added calcium chloride or other chloride based components. It will not promote or contribute to corrosion of reinforcing steel in concrete.

PRECAUTIONS

- CHRYSO Plast 405 should be stored at or above 40°F (5°C). If frozen, thaw
 and agitate thoroughly to return to its normal state before use.
- Do not use pressurized air for agitation.
- CHRYSO Plast 405 is compatible with most CHRYSO admixtures if added separately to the concrete mix.

SAFETY

Prior to any use, please read carefully the Safety data Sheet.

PACKAGING

- 55 Gallon Drum (210 L)
- 264 gallon tote (1000 L)
- BLK

