

# TYTRO® RC430

Viscosity Modifying Admixture

## DESCRIPTION

TYTRO® RC430 is a non-corrosive, non-chloride rheology controlling admixture for concrete and shotcrete that accelerates cement hydration, resulting in increased early compressive and flexural strengths. Featuring the latest in nanotechnology, TYTRO® RC430 contains a liquid dispersion of discrete, spherical, uniformly distributed nanometric particles of amorphous silica for use in concrete.

Manufactured to the highest possible standards, TYTRO® RC430 is formulated to comply with the Standard Specification for Chemical Admixtures for Concrete, ASTM C494 Type S Specific Performance. TYTRO® RC430 is supplied as a ready to use liquid that weighs approximately 10.1 lbs/gal (1.21 kg/L)

## ADVANTAGES

- **Concrete**
  - Excellent early and later age strengths
  - Permeability reduction
  - Improved durability
  - Outstanding rheology properties
- **Shotcrete**
  - Enhanced sprayability
  - Lower rebound and dust
  - Reduced cycle time (larger layer thickness)
  - Excellent strength and durability

## Method of Use

### Dosage

- For concrete applications, TYTRO® RC430 addition rates can vary from 2–10 fl oz/100 lbs (130–650 mL/100 kg), with a typical range of 3-6 fl oz/100 lbs (200-400 mL/100 kg) of cementitious materials.
- For shotcrete applications, dosage rates will vary depending on application, mix design and aggregate gradation, but will typically range from 0.5% to 1.5% by weight of total cementitious.
- Addition rates may vary depending on materials, job conditions and desired performance characteristics.

### Additional Usage Recommendations

- TYTRO® RC430 is typically used in concrete applications to increase and provide faster early age compressive and flexural strengths. TYTRO® RC430 is used in shotcrete applications to improve sprayability and pumpability by increasing cohesion, reducing rebound, providing superior bond to rock substrate, and to provide faster early strength development.

### Equipment

- A complete line of accurate, automatic dispensing equipment is available.

### Complimentary Products

The information contained in this technical data sheet is given to the best of our knowledge and the result from extensive testing - which were conducted in order to remain as objective as possible. However, it cannot, in any case, be considered as a warranty involving our liability in case of misuse or any different use of our products, other than those from the "Application" paragraph of this technical data sheet. Some application tests should be carried out before using the product to ensure that the methods of use and conditions of application of the product are satisfactory. Our technical assistance is at the disposal of the users.

# TYTRO® RC430

## Viscosity Modifying Admixture

- TYTRO® RC430 is compatible with most admixtures as long as they are added separately to the concrete mix, usually through the water holding tank discharge line. In general, it is recommended that the product be added to the concrete mix near the end of the batch sequence for optimum performance. Please see [Technical Bulletin TB-0110](#), Admixture Dispenser Discharge Line Location and Sequencing for Concrete Batching Operations for further recommendations. For optimum performance, TYTRO® RC430 should not come in contact with any other admixture before or during the batching process. Different sequencing may be used if local testing shows better performance.
- Pretesting of the concrete mix should be performed before use, and as conditions and materials change in order to assure compatibility, and to optimize dosage rates, addition times in the batch sequencing and concrete performance. For concrete that requires air entrainment, the use of an ASTM C260 air-entraining agent (such as DARAVAIR® or DAREX® product lines) is recommended to provide suitable air void parameters for freeze-thaw resistance. Please consult your Chryso representative for guidance.

### CHARACTERISTICS

Product Nature	Liquid
Color	Clear
Shelf life	12 months
Cl <sup>-</sup> ions content	< 0,100 %
Specific gravity (25°C) in g/ml	1,215
pH (25°C)	10,00

### PACKAGING

- Bulk
- 275 gallon tote
- 55 gallon drum

### PRECAUTIONS

- TYTRO® RC430 should be stored where temperatures remain above 35° F (2° C). Freezing temperatures cause irreversible precipitation of the silica. Continuous exposure to high temperatures will shorten the shelf life of TYTRO® RC430. Avoid storing TYTRO® RC430 in areas where the temperature routinely goes above 110 ° F (43° C).
- Avoid eye and skin contact and wear rubber gloves and goggles. If contact occurs, rinse with plenty of water. In case of eye contact seek medical advice. For further information refer to the Safety Data Sheet (SDS) or contact your local GCP Applied Technologies representative.

### SAFETY

Prior to any use, please read carefully the Safety data Sheet.