

CHRYSO® Optima 258 EMX

High Range Water Reducing Admixture

DESCRIPTION

New generation of High Range Water Reducing Admixture based on proprietary polymer. Specially designed for highly technical ReadyMix concrete, CHRYSO Fluid Optima 258 EMx provides extended slump retention and pumpability to achieve targeted concrete quality and performance on-site. CHRYSO Fluid Optima 258 EMx improves concrete robustness to optimize the mix design cost/performance ratio.

Meets or exceeds the requirements of ASTM C-494 Type A and F

ADVANTAGES

- High Early and Ultimate Strength Performance
- Enhanced Slump Retention
- Reduces Job Site Water Additions
- Improved Flowability
- Allows better utilization of mixes incorporating high volumes of pozzolans such as fly ash
- High SCM usage contributes to the protection of our environment (Reduction of CO₂ emissions encouraged by LEED directives)

FIELDS OF APPLICATION

- All Cement Types
- Precast Concrete
- Ready Mix Concrete
- Post Tensioned and Prestressed Concrete
- Extended Slump Retention
- Self Consolidating Concrete (SCC)
- Very High Early Strength Concrete
- High SCM Replacement
- Segmental Retaining Wall (SRW)

Method of Use

Dosage

- The recommended dosage rate for CHRYSO Fluid Optima 258 EMX is 2 to 7 oz/cwt (130 to 457 ml/100 kg) of cementitious material for a Type A and 7 to 16 oz/cwt (457 to 1045 ml/100 kg) of cementitious material for a Type F.
- CHRYSO Fluid Optima 258 EMX can be added with the initial water or, for optimum performance, on the wetted concrete. It should not be added with or on the dry cement.
- Dosage rates may vary when used in conjunction with other CHRYSO admixtures.
- Trial mixes should be conducted to determine the dosage rate needed.
- Because local job conditions vary, please contact your local CHRYSO sales representative for further assistance if using the product outside the recommended dosage ranges.

CHARACTERISTICS

Product Nature	Liquid
Color	Green
Shelf life	12 months

PRECAUTIONS

- CHRYSO Fluid Optima 258 EMX should be stored at or above 40°F (5°C). If frozen, thaw and agitate thoroughly to return to its normal state before use.
- Do not use pressurized air for agitation.

The information contained in this technical data sheet is given to the best of our knowledge and the result from extensive testing - which were conducted in order to remain as objective as possible. However, it cannot, in any case, be considered as a warranty involving our liability in case of misuse or any different use of our products, other than those from the "Application" paragraph of this technical data sheet. Some application tests should be carried out before using the product to ensure that the methods of use and conditions of application of the product are satisfactory. Our technical assistance is at the disposal of the users. www.chryso.com

CHRYSO Inc. - 3958 Ruger Dr • Royse City • TX 75189 & PO Box 190 • Rockwall • TX 75087 Tél.:+1 (972) 772 6010

TECHNICAL DATA SHEET

CHRYSO® Optima 258 EMX

High Range Water Reducing Admixture

Chryso
Concrete
Solutions

12/11/2024

Cl ⁻ ions content	< 0,100 %
Specific gravity (25°C) in g/ml	1,085 ± 0,000
pH (25°C)	5,00

This product does not contain any purposely added calcium chloride or other chloride based components. It will not promote or contribute to corrosion of reinforcing steel in concrete.

PACKAGING

- 55 gallon drum
- 275 gallon tote
- Bulk

SAFETY

Prior to any use, please read carefully the Safety data Sheet.

- CHRYSO Fluid Optima 258 EMX is compatible with most CHRYSO admixtures if they are added separately to the concrete mix.
- However, it is not recommended for use in concrete containing naphthalene-based admixtures including ProPel AG, or melamine-based admixtures.

The information contained in this technical data sheet is given to the best of our knowledge and the result from extensive testing - which were conducted in order to remain as objective as possible. However, it cannot, in any case, be considered as a warranty involving our liability in case of misuse or any different use of our products, other than those from the "Application" paragraph of this technical data sheet. Some application tests should be carried out before using the product to ensure that the methods of use and conditions of application of the product are satisfactory. Our technical assistance is at the disposal of the users. www.chryso.com

CHRYSO Inc. - 3958 Ruger Dr • Royse City • TX 75189 & PO Box 190 • Rockwall • TX 75087 Tél.:+1 (972) 772 6010