TECHNICAL DATA SHEET

CHRYSO[®]Quad 520 EMx

Multi-Range Water Reducing Admixture

Chryso

Solutions

DESCRIPTION

CHRYSO Quad 520 EMx is the latest generation of Water Reducing Admixture designed to enhance the use of low-cost aggregates such as manufactured sands. CHRYSO Quad 520 EMx provides good workability retention to achieve targeted concrete guality and performance on-site at an optimized cost.

Meets or exceeds the requirements of ASTM C-494 Type A and F

ADVANTAGES

- Allows Use of high proportions of Manufactured Sand
- Improves Finish, Placement and Pumpability .
- Improves Slump Retention

FIELDS OF APPLICATION

- All Cement Types
- Ready Mix Concrete
- Manufactured Sand
- Sands with High Fines

Method of Use

Dosage

- The recommended dosage rate for CHRYSO Quad 520 EMx is 3 to 10 oz/cwt (195 to 652 ml/100 kg) of cementitious material for a Type A and 7 to 20 oz/cwt (546 to 1304 ml/100 kg) of cementitious material for a Type F.
- CHRYSO Quad 520 EMx can be added with the initial water or, for optimum performance, on the wetted concrete. It should not be added • with or on the dry cement.
- Dosage rates may vary when used in conjunction with other CHRYSO admixtures.
- Trial mixes should be conducted to determine the dosage rate needed. .
- Because local job conditions vary, please contact your local CHRYSO sales representative for further assistance if using the product . outside the recommended dosage ranges.

CHARACTERISTICS

Product Nature	Liquid
Color	Brown
Shelf life	12 months
Cl [−] lons content	< 0,100 %
Specific gravity (25°C) in g/ml	1,060 ± 0,000
рН (25°С)	4,50

This product does not contain any purposely added calcium chloride or other chloride based components. It will not promote or contribute to corrosion of reinforcing steel in concrete.

PRECAUTIONS

- CHRYSO Quad 520 EMx should be stored at or above 34°F (1°C). If frozen, thaw and agitate thoroughly to return to its normal state before use.
- Do not use pressurized air for agitation.
- CHRYSO Quad 520 EMx is compatible with most CHRYSO admixtures if they are added separately to the concrete mix.
- However, it is not recommended for use in concrete containing naphthalene-based admixtures including ProPel AG, or melaminebased admixtures.



The information contained in this technical data sheet is given to the best of our knowledge and the result from extensive testing - which were conducted in order to remain as objective as possible. However, it cannot, in any case, be considered as a warranty involving our liability in case of misuse or any different use of our products, other than those from the "Applcation" paragraph of this technical data sheet. Some application tests should be carried out before using the product to ensure that the methods of use and conditions of application of the product are satisfactory. Our technical assistance is at the disposal of the users. www.chryso.com

CHRYSO Inc. - 3958 Ruger Dr • Royse City • TX 75189 & PO Box 190 • Rockwall • TX 75087 Tél.:+1 (972) 772 6010



TECHNICAL DATA SHEET

CHRYSO[®]Quad 520 EMx

Multi-Range Water Reducing Admixture

Prior to any use, please read carefully the Safety data Sheet.

12/11/2024

PACKAGING

- 55 gallon drum
- 275 gallon tote
- Bulk

The information contained in this technical data sheet is given to the best of our knowledge and the result from extensive testing - which were conducted in order to remain as objective as possible. However, it cannot, in any case, be considered as a warranty involving our liability in case of misuse or any different use of our products, other than those from the "Application" paragraph of this technical data sheet. Some application tests should be carried out before using the product to ensure that the methods of use and conditions of application" of the product are satisfactory. Our technical assistance is at the disposal of the users. **www.chryso.com**

CHRYSO Inc. - 3958 Ruger Dr • Royse City • TX 75189 & PO Box 190 • Rockwall • TX 75087 Tél.:+1 (972) 772 6010

